

## KOHLENSTOFF® COLORX 44

### Speciality Carbon Black

#### Product Description

General purpose low structure pigment black offering good covering power for a wide range of tinting applications. This large particle size grade offers good dispersion, better loading. It's a cost-effective pigment offering high loading, excellent opacity, better flow properties and viscosity.

#### Application

- Suitable for variety of coating application such as automotive, general industrial, or architectural
- Web offset cold-set and letterpress printing inks
- Pigment in Sealant system and general dispersion

The dispersibility of COLORX 44 depends on the formulation & equipment used.

Test	ASTM Test Method	Units	Typical Value
BET Surface Area	D-6556	(m <sup>2</sup> /gm)	30
Oil Absorption No. (OAN)	D-2414	(cc/100 g)	70
Tint Strength	D-3265	%	58
Sieve Residue # 325	D-1514	ppm	<50
Heating Loss (as packed)	D-1509	%	<3

#### Packaging

- Product Form: Powder
- Regional Availability: Global
- Bag Packaging Options: 10 & 20 kg paper bags

#### Disclaimer:

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and Himadri Speciality Chemical Ltd. disclaims all warranties express or implied, including merchantability or fitness for a particular purpose as to (i) such information, (ii) any product or (iii) intellectual property infringement. In no event is Himadri Speciality Chemical Ltd. responsible for, and does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

**Corporate Office:** Ruby House, 8, India Exchange Place, 2<sup>nd</sup> Floor, Kolkata –700 001, West Bengal, India  
Tel:+91 33 2230 4363 | E-mail: [carbonblack@himadri.com](mailto:carbonblack@himadri.com) | Web: [www.himadri.com](http://www.himadri.com)